

VERNASCA - MERINO - CATANIA - LUGANO - HANNOVER

TESTS		TEST METHOD	TEST SPECIFICATIONS
Total Weight (gr/sqm)		IS:7016 P-1	790±5%
Thickness (mm)		IS:7016 P-1	1.15±0.10
Breaking Strength	Warp	IS:7016 P-2	20 Min.
(Kg/5cm)	Weft		12 Min.
Elongation	Warp	IS:7016 P-2	30 Min.
(%)	Weft		120 Min.
Tear Strength	Warp	IS:7016 P-3	1.5 Min.
(KGF)	Weft		1.5 Min.
Double Seam Resistance	Warp	SATRA TM 165	300.0 Min.
(N/5CM)	Weft		120.0 Min.
Adhesion	Warp	ISO 2411	3.0 Min.
(Kg/5cm)	Weft		2.0 Min.
Abrasion / Martindale	Cycles	ISO 5470-2	250 000 Cycles
Bally Flex	Cycles	ISO 5402	100 000 Cycles
Flammability	mm/minute	FMVSS 302	100 MAX.
Flammability	--	Regulation No.118:03 (R118.02 Annexes 6, 7 & 8)	PASS
Flammability	--	BS EN 1021-1+2	PASS
Cold Crack Resistance at -30°	--	FTMS 191A-5874	No crack
UV-Resistance	--	ASTM G154	500Hrs
Light fastness	Blue scale	BS EN ISO 105 B02	5
Width			140cm
Roll Length			30 Meters
Backing			120gr Polyester/Cotton